

Technical Report No: 70.400.09.144.01-00/01

Date: Feb.26, 2009



China

Client: Shanghai Fuyu Mesh Co., Ltd.
538 Jian Chuan Road
Shanghai
P. R. China

Contact person: Mr. Miaofu Zhang

Test subject: Refer to Page 2

Sample provided by: Shanghai Fuyu Mesh Co., Ltd.

Date of sample received: Feb. 20, 2009

Date of tests started: Feb. 23, 2009




Purpose of examination: Phthalate Content

Test method: With reference to US EPA3546:2000 & EPA8270D:2007,
Analysis was performed by GC-MS.

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.



Tested sample description:

No.	Tested sample	Supplier	Picture
001	Teslin(gray) 特斯林(灰色)	Shanghai Fuyu Mesh Co., Ltd.	
002	Teslin(blue) 特斯林(蓝色)	Shanghai Fuyu Mesh Co., Ltd.	
003	Teslin(gray white) 特斯林(灰白色)	Shanghai Fuyu Mesh Co., Ltd.	

Remark: According to Directive 2005/84/EC of the European parliament.

Technical Report No: 70.400.09.144.01-00/01

Date: Feb.26, 2009



China


Test Data:

Parameter	Unit	MDL	001	002	003
Di-(2-ethyl-hexyl) phthalate, DEHP	%	0.003	ND	ND	0.014
Di-butyl phthalate, DBP	%	0.003	0.008	0.009	0.008
Butyl-benzyl phthalate, BBP	%	0.003	ND	ND	ND
Sum of DEHP, DBP & BBP	%		0.008	0.009	0.022
Di-iso-nonyl phthalate, DINP	%	0.01	ND	ND	ND
Di-iso-decyl phthalate, DIDP	%	0.01	ND	ND	ND
Di-n-octyl phthalate, DNOP	%	0.003	ND	ND	ND
Sum of DINP, DIDP & DNOP	%		ND	ND	ND
Conclusion:			Pass	Pass	Pass

Remark:

1. Limit for **sum of DEHP, DBP & BBP**: < 0.1% by weight
2. Limit for **sum of DINP, DIDP & DNOP**: < 0.1% by weight
3. MDL= Method Detection Limit
4. ND = Not Detected (<MDL)

Engineer:


Ms. Ju Jiaqin
Chemical Department

Checked by:


Dr. Lai Xianghua
Chemical Department

Jiangsu TUV Product Service Ltd.
Shanghai Branch

Jiangsu TUV Product Service Ltd, Shanghai Branch
Chemical Department
No. 88 Heng Tong Road, Shanghai, China
Phone: 0086/21/6141-0123; Fax: 6140-8600

Technical Report No.: 70.400.09.144.01-00/01

Feb.26, 2009
Page 3 of 3